

# ROMAN™

## Fast Setting

## Concrete

**PREMIUM FAST SETTING CONCRETE** is a quality blend of portland cement, graded sand, coarse aggregate and special additives. It is designed to be used in applications at least 2 inches thick. Especially designed for easy and fast setting of posts & poles without bracing, as well as rapid setting of slabs, walks, steps and footings. It's a high early concrete that exceeds the requirements of ASTM C 387.

### COMPRESSIVE STRENGTH:

3 day	2,500 psi (17 MPa)
7 day	3,500 psi (24 MPa)
28 day	5,000 psi (34 MPa)

### MIXING:

One 50 lb. (22.7 kg) bag will require up to 3 quarts (2.8 L) of water. Thoroughly mix the contents of the bag with approx. 2 quarts (1.9 L) of water, adding the remaining water a little at a time if the mix is too stiff. *Adding too much water will weaken the mix and may cause cracking in the surface.*

### FINISHING:

Use a screed or straight edge to level the surface. Newly poured concrete should set for about an hour or until the surface water begins to disappear before finishing. Trowel to a smooth finish, but do not overwork the surface. *Over-troweling or finishing the surface too soon can lead to scaling, cracking or dusting of the surface.*

### CURING:

Concrete cures under proper moisture and temperature conditions. It's important to keep the surface damp for several days after placement. Methods include misting, applying a curing agent or placing plastic over the surface. Protect the concrete from freezing for at least 24 hours after placement.

### COVERAGE:

One 50 lb. bag will yield approximately .38 cubic feet.

### ITEM/ UPC:

# 41462/ 8-99002-41462-1

#### SAFETY:

Before using this product, read the Material Safety Data Sheet (MSDS).

#### WARNING:

Wear protective clothing and equipment as needed. Read specific warnings on the package for inhalation, eye and skin contact. **KEEP OUT OF REACH OF CHILDREN.**

# Technical Data 41462



American Dry Mix 200 Frankfurst Ave. Baltimore MD 21225 [www.americandrymix.com](http://www.americandrymix.com)